



www.antiseize.com

# POLY-TEMP<sup>®</sup> JOINT SEALANT

## 100% PTFE- Joint Sealant

### Product Description

**POLY-TEMP<sup>®</sup> JOINT** is a 100% expanded PTFE/UHF gasket material. It comes in a soft, pliable ribbon with a self-adhesive tape applied to one side. Poly-Temp<sup>®</sup> Joint is a tough, flexible, and economical universal gasket that replaces cut gaskets in a variety of regular and severe service applications. It will not deteriorate with age, is unaffected by common chemicals, withstands pressures up to 3,000 psi and temperatures -450<sup>o</sup> to +600<sup>o</sup>F (-268<sup>o</sup>C to +316<sup>o</sup>C). This unique material is highly compressible and fills severe irregularities in sealing surfaces.

### Features & Benefits

- Self-adhesive, easy to work with
  - Flanges part easily
  - No re-torquing required
  - Will not deteriorate with age
  - Resists cold flow and creep
  - Meets FDA requirements
  - Reduces inventory of cut gaskets
  - UL recognized component
- Excellent resistance to most chemicals

### Applications Include

Flanges, rough or irregular surfaces, Pump and Compressor Housings, Heat Exchangers, Manway Covers, FRP Vessels, Steam Vessel Flanges, Boilers and Heat exchangers , Concrete Lids, Glass Joints, Food Service and Processes.

### Acceptance/Approvals

**FDA** - PTFE Joint Sealant meets FDA requirements: PTFE - FDA21 CFR177.1550. Adhesive - FDA21 CFR175.105

**DVGW** - German Federation of Gas and Water Technology - According to DVGW No. 11G/Dr. Dri-PG, PTFE Joint Sealant is suitable for the gas supply at internal pressure up to 232 psig (16bar) in the temperature range from 14°F (-10°C) to 122°F (50°C).

**BAM** - German Institute for Material Research and Test - According to BAM No. 13621/87 4-4625,

there is no reflection against the usage of PTFE Joint Sealant for the Oxygen Supply, sealing the flanges made of copper, copper alloy or steel at internal pressure up to 580 psig (40bar) in the temperature up to 140°F (60°C).

**TUV** - Technical Supervisory Federation of Bavaria in German, Materials and Structural Engineering Division, Quality Monitoring - According to TUV No. 191604, MP3/7381, the characters of the sealing values are as per Chart I and Chart II.

### Typical Properties

Property	Value
Temperature Range	-450°F to +600°F(-268° to +316°C)
Pressure Range	Up to 3000 psi
Heat of Combustion	1434 + 100cal/g
Specific Gravity	0.45-0.55, compressed to 2.0-2.1
Auto ignition Temp	939 ± 100°F
Thermal Conductivity	0.2 BTU/hr-ft @ 0°C
Modulus of Elasticity	500psi @ 73°F
Chemical Compatibility	Inert except with elemental fluorine and alkali metals
Coefficient of Friction	0.2
Matrix Tensile Strength	3000psi - 6800psi
Toxicity	Non-Toxic
Seals subject to radiation exposure	Exposed to 17 Megarads of gamma radiation on steel flanges with no loss of seal
RoHS 3	Compliant
REACH SVHC	Compliant

### Cautions

Read all information on labels and Safety Data Sheets prior to use. All products should be tested and evaluated for a particular purpose prior to use. This sheet provides information and data is based on information we believe reliable. You should thoroughly test any application and independently conclude satisfactory performance before final application.



www.antiseize.com

# POLY-TEMP<sup>®</sup> JOINT SEALANT

## 100% PTFE- Joint Sealant

### Size Recommendations

#### Size Selection Reference

150-300lb. ANSI Flanges	Use This Size
1/2"	1/8"
3/4" - 1 1/2"	3/16"
2" - 4"	1/4"
5" - 8"	3/8"
10" - 16"	1/2"
18" - 24"	5/8"
24" - 36"	3/4"
36" plus	1"

#### Non-Standard or Special Size Flanges

Sealing Width	Use This Size
1/8" - 1/4"	1/8"
5/16" - 3/8"	3/16"
7/16" - 5/8"	1/4"
3/4" - 1"	3/8"
1 1/8" - 1 1/2"	1/2"
1 5/8" - 2"	5/8"
2" - 2 1/2"	3/4"
2 1/2" plus	1"

Cut material with scissors and apply to sealing surface. Self-adhesive strip will hold firmly in place.

### Product Limited Warranty

This information is based on information we believe to be reliable and accurate, but no guarantee of its accuracy is made for a particular application. We urge and recommend that Users pretest their application prior to incorporating the product into use and assume that the User will conduct such testing. Also see warranty statement on website.

### GHS compliant

**GHS Panel**  
**Classified as Non-Hazardous under**  
**HazCom 2012(OSHA GHS)**  
**Read SDS for additional information**

### Available In:

<u>1mm x 100'</u> 28001	<u>1mm x 1000'</u> 28301	<u>1/8" x 100'</u> 28003	<u>1/8" x 1000'</u> 28303	<u>3/16" x 75'</u> 28005
<u>3/16" x 750'</u> 28305	<u>1/4" x 50'</u> 28007	<u>1/4" x 100'</u> 28107	<u>1/4" x 500'</u> 28307	<u>3/8" x 25'</u> 28010
<u>3/8" x 50'</u> 28110	<u>3/8" x 250'</u> 28310	<u>1/2" x 15'</u> 28014	<u>1/2" x 30'</u> 28114	<u>1/2" x 150'</u> 28314
<u>5/8" x 15'</u> 28017	<u>5/8" x 30'</u> 28117	<u>5/8" x 150'</u> 28317	<u>3/4" x 15'</u> 28020	<u>3/4" x 30'</u> 28120
<u>3/4" x 100'</u> 28320	<u>1" x 15'</u> 28025	<u>1" x 30'</u> 28125	<u>1" x 75'</u> 28325	

POLY-TEMP<sup>®</sup> IS A REGISTERED TRADEMARK OF ANTI-SEIZE TECHNOLOGY

**ANTI-SEIZE TECHNOLOGY**

2345 N. 17th AVE. • FRANKLIN PARK, IL 60131-3432  
847-455-2300 • [www.antiseize.com](http://www.antiseize.com)